

DIY Products ARALDITE INSTANT Technical Data Sheet

Reviewed: 06.06.2015



DESCRIPTION

ARALDITE INSTANT is a multi-purpose, ultra-fast 2 component clear epoxy adhesive supplied in a syringe. It is a strong, long lasting, solvent free adhesive which is water resistant and can be painted or sanded. **Sets in 90 seconds**.

ADVANTAGES

- Extra strong bonding
- Ultra-fast
- Clear and colourless
- Easy application
- Bonds a variety of materials
 Temperature resistant (-30°C +70°C)
- Temperature resistantHumidity resistant
- Sandable and paintable
- Sandable and paintable
 Fills uneven breaks
- Withstands rough handling
- 100% solid content
- Solvent free

APPLICATIONS

ARALDITE INSTANT bonds a variety of materials including metal, wood, ceramics, masonry, glass, dry concrete, chipboard, leather, cardboard, most hard plastics, fabrics and rubbers (not suitable for polyethylene, polypropylene, Teflon, expanded polystyrene).

IMPORTANT: ARALDITE INSTANT is not suitable for bonding rear-view mirrors to car windscreens. Do not use for items, which may contain food or drink, as the joint however secure and clean it may appear, may entrap bacteria from the environment. Not intended for repairs on safety critical items e.g. rotating parts of hover mowers. Please note that some items are molded from polymers such as polythene or polypropylene, for example, and are simply not designed for repair. Repair may not be viable or would need specialist chemical treatment to achieve a bond.

INSTRUCTIONS FOR USE

- 1. Make sure surfaces are dry, clean and free from dust, dirt and grease. For even better bonding slightly roughen surfaces with sandpaper.
- 2. To take best advantage of the ultra-fast set, prepare the substrates carefully then check that you can hold them together for a couple of minutes until the adhesive is set.
- **3.** Remove the cap from the center of the plunger so that the syringe may be sealed after use. Snap off the tab, to use.
- **4.** Dispense equal volumes of resin and hardener onto a clean disposable surface. Mix well for 20 seconds, by stirring and folding with a plastic palette knife. It is important to ensure a thorough mix. Reseal syringe as soon as possible.
- 5. Apply the mixed adhesive to both surfaces of the joint and assemble carefully. A layer of adhesive 0.05 to 0.10 mm thick will normally impart the greatest lap shear strength to the joint.
- 6. Keep the joint supported until set. An approximate guide to support and handling times at room temperature is given below:

Pot life: 90 seconds, approximately at 23°C

Support time: 4 minutes at 23[°]C

Full strength: 2 hours at 23°C

Setting times may be shorter in hot weather. In cold conditions the rate of curing of the mixed adhesive may be slowed down significantly and weak joints may result. For best results, use between 20° C and 25° C.

7. For a perfect finish carefully remove any excess adhesive with a sharp knife before the adhesive has fully hardened.

CLEANING

- Uncured resin/hardener mixtures can be cleaned from tools using cellulose thinners or acetone. Solvents must always be handled with due care as they may be hazardous or flammable. Please note that solvents may attack some rubbers, plastics, painted surfaces, fabrics, etc. Bear this in mind if intending to use solvent to remove excess adhesive, and carry out a preliminary test first.
- Cured adhesive residues can usually be dissolved from tools by soaking in paint stripper Mercola STRIPP & CLEAN.
- The adhesive may be removed from the skin using a suitable proprietary hand cleaner. Contact with the skin should however be avoided. Do not use solvents in contact with the skin. Always open and use adhesive products over a protected surface, and avoid contact with clothing.

REMARKS

Thorough mixing is the key to getting a good cured product. Simply stirring leaves unmixed materials at the margins. Always fold in the edges then re-stir. Cured adhesive may yellow if exposed to sunlight for long periods.

TYPICAL ADHESIVE CHARACTERISTICS

Resin Physical form: Liquid Chemical type: Epoxy resin Formulated Viscosity: 18000 - 45000 mPa·s (25^oC) Solids content: 100% Colour: Colorless Odour: Slight





EVOCHEM S.A. Tzaverdella place 13341, Fyli, Attica, Greece Tel.: 210 5590460, 210 5590155 Fax: 210 5590244 E-mail: info@evochem.gr Website: www.evochem.gr





DIY Products ARALDITE INSTANT

Technical Data Sheet

Reviewed: 06.06.2015

Density: 1.15 g/cm3 (25°C)

Hardener

Physical form: Liquid Chemical type: Formulated Polyamine Viscosity: 10000 - 20000 mPa·s (25°C) Solids content: 100% Colour: Light yellow Odour: Slight Density: 1.14 g/cm³ (25°C)

TECHNICAL CHARACTERISTICS

Colour mixed: Very pale yellow Cured density: 1,15 g/cm³ (25°C) Temperature resistance: -30°C to +70°C depending on conditions of use Water: Not intended for constant immersion Oil and petrol: Good resistance Chemicals: Good resistance Sandability: Sandable when set. Please wear dust mask Paintability: Good, but confirm by test. Fine sanding helps.

BARCODE

7610594000121

STORAGE

Store under dry conditions between 5°C and 25°C

SHELF LIFE 3 years if stored as directed above

PACKAGING

Syringe: 24 ml

PACKAGINGCODE24ml00605

HEALTH AND SAFETY INFORMATION



Causes serious eye irritation. Causes skin irritation. May cause an allergic skin reaction. Toxic to aquatic life with long lasting effects. Read label before use. Keep out of reach of children. If medical advice is needed, have product container or label at hand. Wear protective gloves: > 8 hours (breakthrough time): butyl rubber, Ethyl Vinyl Alcohol Laminate (EVAL). Wear eye or face protection. Avoid release to the environment. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. IF ON SKIN: wash with plenty of soap and water. Dispose of contents and container in accordance with all local, regional, national and international regulations. Hazardous ingredients: reaction product: bisphenol A-(epichlorhydrin); epoxy resin (number



EVOCHEM S.A. Tzaverdella place 13341, Fyli, Attica, Greece Tel.: 210 5590460, 210 5590155 Fax: 210 5590244 E-mail: info@evochem.gr Website: <u>www.evochem.gr</u> average molecular weight < 700), 1,8-diazabicyclo[5.4.0]undec-7ene. Contains epoxy constituents. See information supplied by the manufacturer.

The directives contained in this technical data sheet are the result of our long experience from real life applications and the research testing of our research and development laboratory and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications, which are beyond our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments. We are liable only for our products for being free from faults and of consistent quality. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. The present edition of this technical datasheet automatically cancels any previous ones concerning the same product.



201