



Polyurethane Foams

GOLDFOAM GUN 65Lt

Technical Data Sheet

Reviewed: 27.06.2025

DESCRIPTION

GOLDFOAM GUN is a professional one – component, high yield, low expanding, ready to use polyurethane foam with excellent thermal and sound insulation capabilities. After curing the foam can be trimmed and sanded. It has a minimal expansion after application, higher yield compared to other PU foams and is therefore very economical to use. Its new innovative formula offers rapid curing, saving time during application.

ADVANTAGES

- Higher yield up to +50%
- Fast curing formula
- Lower expansion after application
- Excellent adhesion on most substrates
- High thermal and sound insulation
- Good filling capacities
- Less propellant, user and environmentally friendly

APPLICATIONS

- Sealing & mounting of fire doors and windows
- Fixing and sealing of window and doorframes
- Filling of cavities around pipes or other
- Sealing of all openings in roof constructions
- Fixing of insulation materials and roof constructions
- Thermal and sound insulation
- Sealing and filling around pipes and conduits
- Application of a soundproofing layer
- Improving thermal insulation in cooling systems

INSTRUCTIONS FOR USE

Surface preparation

Moistening the surfaces with a water sprayer improves adhesion and curing speed.

Application

1. Surfaces must be clean, free of dust and grease
2. Shake the can well for at least 30 seconds
3. Fit the application gun firmly on the adapter
4. Hold the can upside-down and extrude the foam by pressing bar
5. Gaps have to be filled partially up to 65% as the foam will expand
6. Protect cured foam from sunlight exposure after application

Caution:

Product suitability testing is recommended.

CONSUMPTION

Each can of 830ml can yield up to 65Lt of cured foam in optimal conditions.

REMARKS

- Avoid contact with uncured foam after application especially at low temperatures.
- Cured PU foam must be protected from UV radiation and high temperatures.
- Before use, all **MEGAFOAM PU Foams** should be stored at room temperature for at least 12 hours.

CLEANING

Fresh foam can be removed with **GUN & FOAM CLEANER** or acetone. Proper cleaning of the gun after each application guarantees long life of the gun. Cured foam can only be removed mechanically.

TECHNICAL CHARACTERISTICS

Base: Polyurethane

Consistency: Stable foam

Curing system: Moisture-cure.

Skin formation (20°C/ 65% R.H.): ~ 7 min.

Cutting time (20°C/ 65% R.H.): 30 – 90min.

Curing rate (20°C/ 65% R.H.): 1h for a 30 mm bead

Shrink: Almost none

Post expansion: Minimal

Cellular structure: 70-80% closed cells

Specific gravity: >20kg/m³ (extruded, fully cured)

Temperature resistance: -40°C until +90°C when cured (up to +140°C for short time periods)

Color: Off White

Fire Class (DIN 4102): B3

Thermal Conductivity (DIN 52612): 0,035 W/(m K)

Water Absorption (DIN 53429): max. 1% Vol.

Application temperature: +5°C up to +35°C.

STORAGE

Store in dry and cool storage conditions at temperatures 5°C - 25°C. Protect from moisture, frost and direct sunlight. **Always store can with the valve pointed upwards.**

SHELF LIFE

At least 18 months in unopened containers, in the above-mentioned storage conditions

PACKAGING

Aerosol cans 830ml

PACKAGING	CODE	BARCODE
830ml	9418	5204094094180

HEALTH AND SAFETY INFORMATION

Consult recent Safety Data Sheet before use.

Evochem®

EVOCHEM S.A.

Tzavardella place 13341, Fyli, Attica, Greece

Tel.: 210 5590460, 210 5590155 Fax: 210 5590244

E-mail: info@evochem.gr Website: www.evochem.gr





Polyurethane Foams

GOLDFOAM GUN 65Lt

Technical Data Sheet

Reviewed: 27.06.2025

The directives contained in this technical data sheet are the result of our long experience from real life applications and the research testing of our research and development laboratory and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications, which are beyond our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments. We are liable only for our products for being free from faults and of consistent quality. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. The present edition of this technical datasheet automatically cancels any previous ones concerning the same product.



Evochem[®]

EVOCHEM S.A.

Tzavardella place 13341, Fyli, Attica, Greece

Tel.: 210 5590460, 210 5590155 Fax: 210 5590244

E-mail: info@evochem.gr Website: www.evochem.gr

