



Tile Adhesives & Grouts

ISOMIX ACRYLIC

Technical Data Sheet

Reviewed: 06.06.2015



DESCRIPTION

ISOMIX ACRYLIC is a cement-based white acrylic adhesive for bonding wall and floor ceramic tiles. It contains high strength Portland cement, carefully selected inert fillers, special additives and resins, which offer excellent adhesion even to difficult surfaces. It shows excellent workability, moisture resistance, increased open time and is qualified as non-slip. It is suitable for interior and exterior use. It is classified as a type C1T adhesive according to EN 12004.

ADVANTAGES

- Excellent adhesive strength
- Excellent workability
- Moisture resistance
- Excellent quality of raw materials
- Exterior and interior use
- Easy, clean and fast application

APPLICATIONS

- Bonding of any kind of tiles on walls or floors on various substrates, such as concrete, plaster, blockwork and most common building surfaces.
- Bonding of light marble and granite tiles.

INSTRUCTIONS FOR USE

Substrate preparation

1. Substrates must be leveled, clean, free of oily residues, loose materials, dust etc.
2. Dampening of the substrate before application is recommended during summer period or for very absorptive surfaces, avoiding the creation of water puddles.

Mixing instructions

1. Add 6,5 – 7,5 kg of water in a clean bucket and add gradually under constant stirring 25kg of **ISOMIX ACRYLIC**.
2. Using a low gear electrical mixer stir well until a uniform viscous mixture is formed.
3. Let the mixture stand for 5 minutes and stir again.

4. The working time of the mixture is 3 - 4 hours. Periodical stirring is advised avoiding the addition of more water. Pot life may vary depending on ambient temperature and humidity.

Application

1. The mixture should be applied uniformly on the surface using a notched trowel - spatula according to the size of the tiles and floor or wall application.
2. The tiles should be fixed by pressing them in the desired position within 10 - 20 minutes in order to avoid skin formation. Less time is required for dry and adsorptive surfaces or under high temperatures.
3. All surplus adhesive must be removed whilst the adhesive is still wet using a dampened cloth or sponge, particularly along the grout lines.
4. Surfaces are ready for grouting within 24 hours for floor applications and 12 hours for wall applications, using **ISOMIX GROUT**.

CLEANING

Remove as much material as possible from tools before cleaning. Clean all equipment immediately after use with soapy water.

REMARKS

- Do not add excess amount of water, as this will decrease adhesive's strength and waterproofing properties.
- Periodical stirring is advised while avoiding the addition of more water.

COVERAGE

Approximately 3 – 4kg of dry mix /m² depending on surface condition.

TECHNICAL CHARACTERISTICS

Form: white cement based powder

Specific gravity of fresh product: 1750 kg/m³

Application temperature: +5°C - +35°C

Compressive strength after 28 days: 9,3 Mpa According to EN 196

Flexural strength after 28 days: 3,5 Mpa According to EN 196

Adhesive strength 20°C: 1,87 N/mm² According to EN 1348

Adhesive strength 70°C: 1,17 N/mm² According to EN 1348

Adhesive strength after immersion in water: 1,10 N/mm² According to EN 1348

Adhesive strength after freeze-thaw: 1,04 N/mm² According to EN 1348

Open time: 20 min

Slip: < 0,2 mm

CE	EVOCHEM S.A. Athens, Attica, Greece
	EN 12004
	ISOMIX ACRYLIC cement base, ceramic tile adhesive
	C1T

Evochem®

EVOCHEM S.A.

Tzavardella place 13341, Fyli, Attica, Greece

Tel.: 210 5590460, 210 5590155 Fax: 210 5590244

E-mail: info@evochem.gr Website: www.evochem.gr





Tile Adhesives & Grouts

ISOMIX ACRYLIC

Technical Data Sheet

Reviewed: 06.06.2015

STORAGE

Store in dry and cool storage conditions at temperatures 5°C - 30°C. Protect from moisture, frost and direct sunlight.

SHELF LIFE

At least 12 months in the above mentioned storage conditions. Products should remain in their original unopened sealed bags, bearing the manufacturers batch number.

ELASTIFICATION

ISOMIX ACRYLIC may be elastified by adding 2 – 6 kg of ISOMIX RESIN ACR 300 acrylic resin plus the quantity of water required in order to reach the desired workability. The end product will be most suitable in applications where an increased demand for elasticity and frost resistance is required such as substrates with increased contraction – expansion properties (swimming pools, terraces, floors with under floor heating etc). The end product will be classified as type S1 adhesive according to EN 12002.

PACKAGING

25kg

PACKAGING	CODE	BARCODE
25kg	01751	5204094017516

HEALTH AND SAFETY INFORMATION



Eye Dam. 1: H318 Causes serious eye damage **Skin Irrit. 2: H315** Causes skin irritation **Skin Sens. 1: H317** May cause an allergic skin reaction **STOT SE 3: H335** May cause respiratory irritation **P102** Keep out of reach of children **P261** Avoid breathing dust/fume/gas/mist/vapours/spray **P271** Use only outdoors or in a well-ventilated area **P280** Wear protective gloves/protective clothing/eye protection/face protection **P304 + P340** IF INHALED: Remove person to fresh air and keep comfortable for breathing **P305 + P351 + P338** IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing **P310** Immediately call a POISON CENTER or doctor **P302 + P352** IF ON SKIN: Wash with plenty of water and soap **P333 + P313** If skin irritation or rash occurs: Get medical advice/attention **P362 + P364** Take off contaminated clothing and wash it before reuse **P501** Dispose of the contents/container in accordance with the current legislation on waste treatment **EUH208**: Contains cement portland, chemicals. May produce an allergic reaction. Substances that contribute to the classification: cement portland, chemicals, Calcium dihydroxide

The directives contained in this technical data sheet are the result of our long experience from real life applications and the research testing of our research and development laboratory and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications, which are beyond our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments. We are liable only for our products for being free from faults and of consistent quality. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. The present edition of this technical datasheet automatically cancels any previous ones concerning the same product.



Evochem®

EVOCHEM S.A.
Tzavardella place 13341, Fyli, Attica, Greece
Tel.: 210 5590460, 210 5590155 Fax: 210 5590244
E-mail: info@evochem.gr Website: www.evochem.gr

