



DESCRIPTION

PGP FIBRATED FILLER is ready mixed masonry filler based on acrylic resins and rock wool fibers, suitable for both interior and exterior use. It is suitable for filling and coating cracks and holes on walls, ceilings, floors and doors. Due to its unique formulation fills cracks easier with less shrinkage and withstands bigger surface movement and vibrations than conventional elastic fillers. May be applied on most usual building surfaces.

ADVANTAGES

- Ready mixed formula
- Fortified with rock wool fibers
- Excellent workability, offers a tough smooth finish
- Dries fast and can be easily sanded
- Presents very low shrinkage – does not crack
- Forms a non-absorbent white substrate, ready for painting
- Interior and exterior use
- Rapid and clean application

APPLICATIONS

- It is suitable for filling cracks and joints of interior and exterior walls and ceilings prior to the final coat.
- It is suitable for plaster, smooth concrete surfaces, aerated concrete blocks, plasterboards, cement boards etc.

INSTRUCTIONS FOR USE

1. Surfaces must be dry and clean from dust, grease and loose particles and other contamination
2. For deeper cracks or joints application of water-based acrylic primer is necessary
3. Apply with a spatula or spreader
4. Press the filler onto the surface to a maximum depth of 5mm
5. For deep cavities 0,5 – 2cm use plastic or fiber reinforcing net.
6. Allow each layer to dry (approximately 1 hour) before applying the next.
7. Fill hole proud to allow for sanding and finish with a wet knife
8. Once dry, sand to a smooth finish
9. The final surface may be primed and painted
10. Close lid immediately after use to prevent drying

It is advisable to perform a suitability test prior to full scale application

REMARKS

- Do not use to fill plastics or metals
- Do not apply externally when rain is imminent (within 5 hours of application)
- Do not apply at temperatures (ambient and surface) below 5°C
- Not suitable for repairs to permanently wet areas

CLEANING

Remove as much material as possible from tools before cleaning. Clean all equipment immediately after use with warm water.

TECHNICAL CHARACTERISTICS

Type: Acrylic surface filler with rock wool fibers

Consistency: Thixotropic paste

Colour: Light gray

Smell: Characteristic of acrylic resin

Specific gravity: 1650 - 1700 kg/m³ 25°C

Method of application: Spatula

Curing System: Physical drying

Drying times: May be sanded in 3 - 4 hours, depending on ambient temperature

Application temperature: 10°C - 35°C

STORAGE

Store in dry and cool storage conditions at temperatures 5°C-30°C. Protect from moisture, frost and direct sunlight.

SHELF LIFE

At least 12 months in unopened containers. Products should remain in their original unopened containers, bearing the manufacturers batch number.

PACKAGING

500gr, 1kg, 4,5kg

PACKAGING	CODE	BARCODE
500gr	7167	5204094071679
1kg	7168	5204094071686
4,5kg	7169	5204094071693

HEALTH AND SAFETY INFORMATION

EUH208: Contains Mixture of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H -isothiazol-3-one [EC no. 220-239-6] (3:1). May produce an allergic reaction



Fillers

PGP FIBRATED FILLER

Technical Data Sheet

Reviewed: 06.06.2015

The directives contained in this technical data sheet are the result of our long experience from real life applications and the research testing of our research and development laboratory and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications, which are beyond our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments. We are liable only for our products for being free from faults and of consistent quality. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. The present edition of this technical datasheet automatically cancels any previous ones concerning the same product.



Evochem®

EVOCHEM S.A.
Tzavardella place 13341, Fyli, Attica, Greece
Tel.: 210 5590460, 210 5590155 Fax: 210 5590244
E-mail: info@evochem.gr Website: www.evochem.gr

