

Adhesives & Sealants SUPER CONTACT MONTAGE

Technical Data Sheet

Reviewed: 06.08.2019

DESCRIPTION

SUPER CONTACT MONTAGE is a solvent-based, ready to use assembly adhesive, based on neoprene rubber. It replaces the use of nails and screws in many applications.

ADVANTAGES

- Extra strong bonding
- Fast application
- Instant grab
- Bonds on uneven substrates
- Weather and moisture resistant
- Interior and exterior use

APPLICATIONS

MERCOLA

ΚΟΛΛΑ

ΣΤΕΡΕΩΣΗ ΞΥΛΟ - ΠΕΤΡΑ ΜΕΤΑΛΛΑ - ΚΕΡΑΝ

ASSEMBLY

ADHESIVE

COBATERI CANAAIA KAM

ALAGOPA FEAR

• Assembling and fixing in building and renovation projects.

• Suitable for bonding and fixing door signs, profiles, architraves, skirting boards, panels, wooden floor panels, cable ducts, sills, ceramic tiles, bricks, natural and artificial stones, metal, cork etc.

• Bonding chipboard and uPVC panels on brickwork, stone render and concrete.

INSTRUCTIONS FOR USE

1. Surfaces must be clean, free of dust and grease.

2. Apply adhesive with caulking gun.

3. Apply dots or stripes of approx. 20 cm apart.

4. Place the component into place by shoving and pushing firmly.

5. For faster bonding apply glue on both parts. Place the component into place and take it apart again. Let dry for approximately 5 minutes and press on again firmly. If necessary use a rubber hammer.

6. If necessary (for heavy materials) support until the adhesive is fully cured (24 hours).

A suitability test is recommended

REMARKS

SUPER CONTACT MONTAGE is not recommended for polystyrene, PE, PP, Teflon, bituminous surfaces and other solvent sensitive surfaces. For expanded and extruded polystyrene use PU 501 MONTAGE.

CLEANING

Clean all equipment with brush solvent or acetone immediately after use.

CONSUMPTION

300-1000 gr/m² or 25-40 gr/m

TECHNICAL CHARACTERISTICS

Base: Neoprene Colour: Yellow Density: 1,34 gr/ml Application temperature: +5°C - +30°C Solids: 65% Open time (23°C/ 55% R.F.): 5-10 min. Final adhesion: 24h Temperature Resistance: -20°C to +70°C. Tensile strength (4h / 20°C): 6,5 kg/cm² Tensile strength (168h / 20°C): 24 kg/cm² Application temperature: +5°C - +30°C

STORAGE

In a cool and dry place at temperatures between +5°C - +25°C

SHELF LIFE

10 months in unopened packaging in the above mentioned storage conditions

PACKAGING

Cartridges 280ml

PACKAGING	CODE	BARCODE
280ml	04218	5204094042174

HEALTH AND SAFETY INFORMATION



Aquatic Chronic 3: H412 Harmful to aquatic life with long lasting effects Eye Irrit. 2: H319 Causes serious eye irritation Flam. Liq. 2: H225 Highly flammable liquid and vapour STOT SE 3: H336 May cause drowsiness or dizziness P101 If medical advice is needed, have product container or label at hand P102 Keep out of reach of children P210: Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking P264: Wash thoroughly after handling P280: Wear protective gloves/protective clothing/eye protection/face protection P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing P370+P378: In case of fire: Use ABC powder extinguisher to extinguish. P501: Dispose of contents and / or their container according to the separated collection system used in your municipality EUH066 Repeated exposure may cause skin dryness or cracking. Substances that contribute to the classification: 2-butanone CAS: (78-93-3); Hydrocarbons, C6-C7, n-alkanes, isoalkanes, cyclics, <5% nhexane







Page. 1



Adhesives & Sealants
SUPER CONTACT MONTAGE

Technical Data Sheet

Reviewed: 06.08.2019

The directives contained in this technical data sheet are the result of our long experience from real life applications and the research testing of our research and development laboratory and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications, which are beyond our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments. We are liable only for our products for being free from faults and of consistent quality. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. The present edition of this technical datasheet automatically cancels any previous ones concerning the same product.





EVOCHEM S.A. Tzaverdella place 13341, Fyli, Attica, Greece Tel.: 210 5590460, 210 5590155 Fax: 210 5590244 E-mail: info@evochem.gr Website: www.evochem.gr

