



Enamel Paints

SWAN VELATURA AQUA

Technical Data Sheet

Reviewed: 06.06.2015



DESCRIPTION

SWAN VELATURA AQUA is a fast drying acrylic waterbased undercoat suitable for exterior and interior use. It provides a perfect substrate for wooden surfaces and walls for finishing with SWAN solvent or waterbased enamel paints. It offers superior coverage and whiteness, smooth finish and easy sanding.

ADVANTAGES

- Waterbased – environmentally and user friendly
- Excellent adhesion
- Excellent coverage
- Smooth finish
- Easy sanding
- Lead free

APPLICATIONS

- It is ideal for wooden surfaces such as doors, windows, cupboards etc.
- It is suitable for walls and ceilings

INSTRUCTIONS FOR USE

Surface Preparation

1. All surfaces should be sanded, dry and clean from dirt, grease, loose paint etc.
2. For wooden surfaces all knots should be scraped and treated with wood preservative XYLOFARM. Then leveled with TEMPO wood putty or polyester putty PLASTIC METAL.
3. Fill minor defects on walls with acrylic filler STANDARD, for large gaps use SUPER LITE filler. In order to smooth new surfaces use ISOMIX WALL STUCCO.

Application

Apply two coats of **SWAN VELATURA AQUA** on well-leveled surfaces. Dried surfaces should be sanded prior to application of the final coat.

LEAD STATEMENT

WARNING: Treatment of old surfaces such as dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Lead dust may be released. Lead is toxic. Exposure to lead dust can cause serious illness. Wet sanding/flattening should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.

CLEANING

Clean all equipment immediately after use with soapy water.

COVERAGE

10 - 15 m²/lt on smooth surfaces

TECHNICAL CHARACTERISTICS

Type: Acrylic waterbased undercoat for enamel paints.

Colour: White

Specific gravity: 1,38 ± 0,2 gr/cm³ 25°C

Viscosity: 4500 cps 25°C

Method of application: roller, brush or spray

Application temperature: 10°C - 35°C

Thinning: With water 5% for application with brush and roller and 10% for spray

Drying times: normally touch dry after 3 hours depending on environmental conditions. Recoat after 6 - 8 hours.

VOC (Volatile organic Compounds): EU limit value for this product category A/d Interior/ exterior trim and cladding paints for wood and metal: 130 gr/lt (2010). This product contains max 40 g/l VOC

STORAGE

In a cool and dry place at temperatures between +5°C - +25°C

SHELF LIFE

24 months in an unopened packaging in the above mentioned storage conditions

PACKAGING

White 750ml, 2,5Lt

PACKAGING	CODE	BARCODE
Δοχείο 750ml	3147	5204094031475
Δοχείο 2.5Lt	3143	5204094031437

HEALTH AND SAFETY INFORMATION

EUH208: Contains Mixture of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H -isothiazol-3-one [EC no. 220-239-6] (3:1). May produce an allergic reaction

Evochem®

EVOCHEM S.A.

Tzavardella place 13341, Fyli, Attica, Greece

Tel.: 210 5590460, 210 5590155 Fax: 210 5590244

E-mail: info@evochem.gr Website: www.evochem.gr





Enamel Paints

SWAN VELATURA AQUA

Technical Data Sheet

Reviewed: 06.06.2015

The directives contained in this technical data sheet are the result of our long experience from real life applications and the research testing of our research and development laboratory and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications, which are beyond our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments. We are liable only for our products for being free from faults and of consistent quality. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. The present edition of this technical datasheet automatically cancels any previous ones concerning the same product.



Evochem®

EVOCHEM S.A.
Tzavardella place 13341, Fyli, Attica, Greece
Tel.: 210 5590460, 210 5590155 Fax: 210 5590244
E-mail: info@evochem.gr Website: www.evochem.gr

