



## Adhesives & Sealants

# MEGASIL

### Technical Data Sheet

Reviewed: 06.06.2015



#### DESCRIPTION

**MEGASIL** is a high quality professional grade, elastic 100% silicone one component joint sealant. It is suitable for all usual building applications.

#### ADVANTAGES

- Stays elastic after curing
- Excellent adhesion properties
- Colourfast
- Fast curing
- Very easy application
- Mildew resistant
- UV resistant

#### APPLICATIONS

- Building and construction joints
- Glazing
- Sanitary installations
- Sealing in cold storage rooms and containers
- Sealing in air condition systems

#### INSTRUCTIONS FOR USE

1. Surfaces must be clean, free of dust and grease
2. Porous surfaces should be primed with ISOCRYL PRIMER DUR, ISOCRYL PRIMER DUR AQUA or PRIMER PU 900
3. Use caulking gun
4. Repair with **MEGASIL**
5. Finish with soapy water before skin formation

A suitability test is recommended  
Not suitable for PVC, PE, PP, PTFE and bituminous substrates

#### JOINT SIZE

**Minimum Width:** 5mm  
**Maximum Width:** 30mm  
**Minimum Depth:** 5mm  
**Recommendation:** 2 X depth = width

#### REMARKS


Due to the acetic character some metals (copper, lead) can be attacked. **MEGASIL** is not recommended for use on natural stones, marble etc. For applications on natural stones and marble use ALL FIX M-S POLYMER instead.

#### CLEANING

Clean all equipment with white spirit immediately after use

#### TECHNICAL CHARACTERISTICS

**Base:** Polysiloxane  
**Colour:** Transparent, White, Black, Brown, Gray  
**Consistency:** Paste  
**Curing System:** Moisture Cure  
**Skin formation (20°C/ 65% R.H.):** 15 - 25min  
**Curing Rate (20°C/ 65% R.H.):** 1-2mm /24h  
**Hardness (DIN 53505):** 18 Shore A  
**Specific gravity (DIN 53479):** 0.97 gr/ml (Transparent)  
**Temperature Resistance:** -20°C - +100°C  
**Maximum allowed Distortion:** 20%  
**Elasticity Modulus 100% (DIN 53504):** 0,35 N/mm<sup>2</sup>  
**Application temperature:** +5°C - +35°C.



#### STORAGE

In a cool and dry place at temperatures between +5°C - +25°C

#### SHELF LIFE

12 months in unopened packaging in the above mentioned storage conditions

#### PACKAGING

Cartridges 280ml Transparent, White, Black, Brown, Gray

PACKAGING	CODE	BARCODE
280ml Transparent	54002	5204094040064
280ml White	54000	5204094040057
280ml Brown	54004	5204094040040
280ml Black	54001	5204094040019
280ml Gray	54003	5204094040033

#### HEALTH AND SAFETY INFORMATION

**P101** If medical advice is needed, have product container or label at hand **P102** Keep out of reach of children **P103** Read label before use **P501** Dispose of the contents/containers in accordance with the current legislation on waste treatment

# Evochem®

EVOCHEM S.A.  
 Tzavredella place 13341, Fyli, Attica, Greece  
 Tel.: 210 5590460, 210 5590155 Fax: 210 5590244  
 E-mail: info@evochem.gr Website: www.evochem.gr





## Adhesives & Sealants

# MEGASIL

Technical Data Sheet

Reviewed: 06.06.2015

The directives contained in this technical data sheet are the result of our long experience from real life applications and the research testing of our research and development laboratory and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications, which are beyond our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments. We are liable only for our products for being free from faults and of consistent quality. Users are responsible for complying with local legislation and for obtaining any required approvals or authorizations. The present edition of this technical datasheet automatically cancels any previous ones concerning the same product.



# Evochem®

EVOCHEM S.A.  
Tzavardella place 13341, Fyli, Attica, Greece  
Tel.: 210 5590460, 210 5590155 Fax: 210 5590244  
E-mail: info@evochem.gr Website: www.evochem.gr

